



DAROTopp® DT25, DAROTopp® XS, DAROTopp® ECO

Self-Levelling Synthetic Anhydrite Topping (Screed/Underlayment) Specification

This Specification has been numbered, organized and formatted in accordance with the Master Format, Section Format and Page Format documents published jointly by Construction Specifications Canada (CSC) and Construction Specifications Institute (CSI).

The Content of this specification is of general order and must be adapted to the specific requirements of a project. It is offered as a guide to experienced and knowledgeable construction professionals who must assume full responsibility for its interpretation and use. DARO Flooring Constructions Inc. is both a material supplier and installer, either through in-house crew or licensed Master Applicators.

The square brackets [] containing texts indicate an option to be considered/inserted by the specifier. Remove brackets and unused options before printing.

PART 1: General

1. SECTION INCLUDES

- A. Supply and installation of self-levelling synthetic (concrete) topping/underlayment over interior structural substrate.

2. RELATED REQUIREMENTS

- A. Finished Floor [Section _____]

SPEC NOTE: DAROTopp® Synthetic topping/underlayment is suitable for receiving any type of floor covering. For light commercial applications or lofts, a polyurethane or epoxy finish may also be used. Once traffic ready, finishing/covering subcontractor to perform moisture test to verify topping surface is ready to accept finishing/covering!

SPEC NOTE: Prior to application of **some** floor coverings (vinyl, VCT, etc), DAROTopp® typically requires a light sanding/grinding 10-14 days after application. Consult with DARO for finish recommendations and moisture parameters.

B. Caulking

[Section ———]

3. PRE-INSTALLATION MEETING

- A. Converse with related trades [one] week prior to commencing work of this section [under provisions of] [Division 01-General Requirements] [Section 01 33 19.33].

4. SUBMITTALS

Submit the following in accordance with Section 01 33 00 – Submittal Procedures]:

- A. Product Data: Flowing Synthetic (concrete) topping manufacturer's printed product literature for proprietary materials used in system.
- B. Shop Drawings: Provide CAD drawings showing details, dimensions, extent of work and other data necessary for the satisfactory installation of the products stated herein.
- C. Samples: [Duplicate] [Triplicate] 150mm x 150mm (6" x 6") size for review showing final colour. Label samples with origin and intended use if necessary.
- D. Manufacturer's Instructions: Pre-Printed material describing installation of product, system or material, including special notices and Material Safety Data Sheets outlining hazards and safety precautions.
- E. Sustainable Design Verification: Third party validation of product performance attesting to material/system life cycle and green building characteristics.

5. QUALITY ASSURANCE

- A. Manufacturer Qualifications: to have minimum of 10 projects of similar type in the past 5 years.
- B. Installer Qualifications: Applicator to be registered by synthetic topping manufacturer using manufacturer's approved pumping equipment.

6. DELIVERY, STORAGE AND HANDLING

- A. Ensure materials, as transported using ready-mix vehicles, are provided to site in timely fashion ready for installation.
- B. Handle ready-mix product in manner to prevent adulteration, deterioration and soiling and in accordance with topping manufacture's instructions.
- C. Remove and replace damaged products at own expenses and to satisfaction of [Consultant] [Engineer].

7. SITE CONDITIONS

- A. Ambient Conditions: Ensure Building interior is enclosed and maintained at temperatures no lower than 5°C (40°F) and no higher than 30°C (90°F); and outside temperature no lower than -5°C (23°F).
- B. Any exception to the above parameters to be approved by topping manufacturer.
- C. Keep windows and doors closed to avoid drafts initial 48 hours period after pumping.
- D. Avoid “chimney effect” from stairwell or other vertical influences to prevent accelerated drying.
- E. Cover any window that allow direct sunlight onto installation areas during drying period and only if direct sunlight heats topping and interior temperature to higher than 30°C (90°F) typically influenced by huge windows or glass facades.
- F. Avoid continues exposure to high interior temperatures outside of parameters outlined above, to avoid completely altering area climate.

SPEC NOTE: Brickwork, plastering and similar operations tend to dry quickly thereby absorbing additional moisture from synthetic (concrete) topping and influence drying characteristics.

- G. Advise [project manager] [building owner] of required climate and physical conditions of site to avoid possibility of cracks in flooring if manufacturer guidelines are not followed.

8. SPECIAL WARRANTY

- A. Provide a written and signed Warranty in the name of the Owner for a period of two (2) years from the date of Substantial Performance of the work.
- B. The Warranty to cover performance of synthetic (concrete) topping.

PART 2: Products

1. MANUFACTURER

- A. Acceptable Synthetic Anhydrite Topping Manufacturer: **DARO** Flooring Constructions Inc., 6201 Hwy 7, Unit # 4, Vaughan Ontario, L4H 0K7 Tel: 905.264.2202; Fax: 905.264.8646; Toll Free:1.877.760.3276; Email: Info@daroflooring.com; Web: www.daro-flooring.com;
- B. Substitutions: Alternative or substitution products or materials not permitted.

2. DESIGN CRITERIA

- A. Synthetic and anhydrite topping to provide compressive strength, after 7 days 80%, after 28 days of [20-40 MPA].

SPEC NOTE: Strength class is dependent upon project requirements. Consult with D^AR^O for recommendations.

3. MATERIALS

- A. Synthetic Anhydrite Topping Binder: D^AR^OTopp® floor underlayment and synthetic anhydrite compound based on specially treated calcium sulphate ingredients.
- B. Portland cement as per manufactures mix-design.
- C. Water: Potable, free from impurities.
- D. Bonding agent water based or epoxy based.

SPEC NOTE: Bonding agent dependents upon project requirements. Consult with D^AR^O for recommendations.

4. MIXES

- A. Mix synthetic (concrete) topping ingredients strictly in accordance with manufacturer's instructions and under the supervision of the manufacturer's quality control specialist to required [C-20] [C-30] mix design prior to ready-mix truck delivery to site.
- B. Using hangermann funnel, provide on site flow (sump) test to ensure mix proportions and methods have been adhered to, prior to pumping.
- C. Retain test-prisms of ready-mix for every delivery. Copy of delivery notice to accompany sample for quality control purposes, and to include flow rate at both plant and site, amount of any additional water if required, arrival time, and time of installation.
- D. Monitor ingredients with regular sieving. Any changes made to mix formula or gradation to be supervised by manufacturer's quality control specialist.
- E. At ready-mix plant, check moisture content of sand daily to ensure proper water requirement, Recycled water not permitted.
- F. Prior to loading ready-mix truck, ensure mixer is clean and free of water residue, salt or chlorides.
- G. After loading topping onto ready-mix truck, check consistency of mixture. Ensure flow dimension on manufacturer's measuring disc is 330 mm (+/- 10mm). In the event of increased distance or time to sire, increase dimension by 10mm to 20mm only on advice of manufacturer's quality control specialist.
- H. During warmer weather, employ higher water content of 350mm flow diameter at plant and 360mm flow diameter for longer distances to site

5. FINISH

- A. Natural, light beige integral colour.

PART 3: Execution

1. EXAMINATION

- A. Before installation, examine structural alignment, smoothness and evenness of subfloor. Notify [contractor] in writing if subfloor does not comply with requirements of this section.
- B. Ensure subfloor is free of mud, oil, grease and other contaminants prior to starting work of this Section.
- C. Verify items provided by other trades are properly installed.
- D. Commencement of work will imply acceptance of substrate conditions.

2. PREPARATION

- A. Ensure installation area is free of all debris, broom clean and dry.
- B. Protect surrounding surfaces from damage due to work of this section.

3. INSTALLATION

A. General

1. Install Synthetic (concrete) flooring strictly in accordance with manufacturer's printed instructions.
2. Co-ordinate work with related work.

B. [Base Slab] [Subfloor] Repairs

1. Patch larger cracks, holes and voids with standard concrete or a quick-setting patching material or spray foam (by GC) prior to installing floor system.

C. Field Isolation (Expansion) Joints

1. Ensure joints continue completely through the synthetic (concrete) topping and are of uniform width if required.
2. Locate expansion joints where shown on shop drawings.

D. Synthetic (Concrete) Topping

1. Ensure topping is mixing at normal speed and at optimal pumping consistency on ready-mix truck before installing.
2. Using topping manufacturer approved pump, apply synthetic topping evenly over floor surface holding hose reasonably close to ground.
3. Ensure topping does not “leak” through substrate.
4. Remove any levelling blocks that may have been used directly after pumping and before “dubbing” procedures.
5. Maintain ambient relative humidity of 50% or greater above topping during first 48 hours after application, avoiding rapid drying or drafts during this period.
6. After 48 hours, in which the floor has had no exposure to direct sunlight or excess drafts, employ accelerated drying procedures as necessary using heating in conjunction with continuous fresh air circulation.

4. SITE QUALITY CONTROL

A. Site Tests

1. Take at least 3 prisms of topping from each concrete truck of day’s pour during application.
2. Test Prisms as recommended by topping manufacturer in accordance with published testing values.
3. Make test results available to [Consultant] [Engineer] upon request.

5. CLEANING

- A. Clean and make good surfaces soiled or damaged by work of this section.
- B. Remove debris and surplus materials upon completion of work.

SPEC NOTE: DAROTopp® is delivered as ready-mix therefore no waste management is required.

6. PROTECTION

- A. After installation, during drying period, protect topping as follows:
 1. Use barriers, markers or signs to limit access to floor areas as necessary.

2. Use temporary wood planking for heavy wheeled or concentrated loads, or access by other trades, subject to the requirements of the work of this Section.

END OF SECTION